



EUCON AIR 30

AIR ENTRAINING AGENT FOR CONCRETE

DESCRIPTION

EUCON AIR 30 is formulated for use as an air entraining admixture for concrete of all types and is manufactured under rigid control which assures uniform and precise performance. EUCON AIR 30 adds microscopic air bubbles in concrete and is acceptable to use in all types of concrete. EUCON AIR 30 does not contain added chlorides and will not promote the corrosion of steel.

PRIMARY APPLICATIONS

- Ready mix concrete
- Structural concrete
- Mass concrete
- Paving concrete
- All exterior concrete subjected to freeze/thaw cycling

FEATURES/BENEFITS

- Provides a stable air void system with proper bubble size and spacing which will increase durability.
- Concrete is made more resistant to de-icing salts, sulfate attack and corrosive water
- Less mixing water can be used per yard (meter) of concrete and placeability is improved
- Minimizes bleeding and segregation of the concrete

TECHNICAL INFORMATION

EUCON AIR 30 is an aqueous solution manufactured from the salt of benzyl sulfonate. It is compatible with concrete mixes containing calcium chloride, water reducing admixtures, retarding admixtures, or high range water reducers.

PACKAGING

EUCON AIR 30 is packaged in bulk, 275 gal (1041 L) totes, 55 gal (208 L) drums and 5 gal (18.9 L) pails.

SHELF LIFE

2 years in original, unopened package.

SPECIFICATIONS/COMPLIANCES

EUCON AIR 30 meets or exceeds the requirements of the following specifications:

- Corps of Engineers Specification CRD C-13
- ASTM Specification C 260
- AASHTO Specification M 154

DIRECTIONS FOR USE

EUCON AIR 30 is typically dosed at a rate of 0.5 to 1.0 oz per 100 lbs (30 to 60 mL per 100 kg) of total cementitious material to entrain 3% - 6% air content. The amount of EUCON AIR 30 will vary depending on type of cement, fineness of sand, temperature, design of the mix, other admixtures, etc. Concrete mixes must be tested regularly to confirm that proper air content is achieved. EUCON AIR 30 should be added directly to the sand to achieve maximum performance.

PRECAUTIONS/LIMITATIONS

- Consult your local Euclid Chemical representative for the proper dosage rate adjustments when using fly ash, slag or high range water reducers.
- Add to the mix independent of other admixtures.
- Excessive air entrainment will lower flexural and compressive strengths so frequent testing is recommended.
- In all cases, consult the Safety Data Sheet before use.

Rev. 10.16

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.