



EUCON HC

WATER REDUCING/SET RETARDING ADMIXTURE

DESCRIPTION

EUCON HC is a water reducing and retarding admixture for concrete. This versatile admixture consists of a modified carboxylate polymer which produces high quality concrete economically. EUCON HC shows improved finishing characteristics when compared to untreated concrete. EUCON HC contains no added chlorides and will not promote corrosion of steel.

PRIMARY APPLICATIONS

- Flatwork concrete
- Architectural concrete
- General purpose ready mixed concrete
- Mass concrete
- Bridge decks
- Hot weather concreting

FEATURES/BENEFITS

Plastic Concrete

- Improves finishability
- Improves workability
- Reduces water requirement
- Extends setting times

Hardened Concrete



- Increases compressive strength
- Reduces permeability
- Improves finished appearance
- Reduces shrinkage
- Increases durability
- Non staining

TECHNICAL INFORMATION

Performance Data

The following test results were achieved using typical ASTM C 494 mix design requirements, 517 lb/yd³ (307 kg/m³) cement content and similar (± 0.5)% air content.

These results were obtained under laboratory conditions with materials and mix designs meeting the specifications of ASTM C 494. Changes in materials and mix designs can affect the dosage response of EUCON HC.



PACKAGING

EUCON HC is packaged in bulk, 275 gal (1041 L) totes, 55 gal (208 L) drums, and 5 gal (18.9 L) pails.

SHELF LIFE

1 year in original, unopened package.

SPECIFICATIONS/COMPLIANCES

EUCON HC meets or exceeds the requirements of:

- ASTM C 494, Type A and Type D
- AASHTO M 194

DIRECTIONS FOR USE

EUCON HC is normally used at dosages of 2 to 8 oz per 100 lb (130 to 520 ml per 100 kg) of cementitious material. Higher dosages are acceptable with prior testing and confirmation of the desired performance with specific materials being used.

EUCON HC should be added to the initial batch water of the concrete mixture. Do not dispense onto dry cement.

PRECAUTIONS/LIMITATIONS

- Care should be taken to maintain EUCON HC above freezing; however, freezing and subsequent thawing will not harm the material if thoroughly agitated. Never agitate with air or an air lance.
- Add to mix independent of other admixtures.
- In all cases, consult the Safety Data Sheet before use.

Rev. 11.14

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.