



APPLICATION ADDENDUM FOR APPLYING EUCO[®] DIAMOND HARD[™] OVER LEVEL TOP

This application addendum applies only to Euco Diamond Hard being applied to Level Top Products after the polishing phase is completed. All other applications should strictly follow the application instructions stated on the Euco Diamond Hard TDS.

APPLICATION (OVER LEVEL TOP POLISH OR LEVEL TOP PC-AGG ONLY)

Air temperature during application must be between 35°F and 100°F (2°C and 38°C). At temperatures below 50°F (10°C), the reaction and “gelling” process of EUCO DIAMOND HARD is slower. In hot or windy conditions, the reaction may take less than the normal 30 minute period. The polished Level Top surface should be dry. Sparingly apply the EUCO DIAMOND HARD to the polished Level Top surface by low pressure sprayer or by pouring directly onto the surface and distributing evenly by microfiber application. Two coats will be necessary. The first coat will be at a coverage rate of 100 – 200 ft²/gal (2.4 – 4.9 m²/L). Do not let the Euco Diamond Hard puddle. If excess EUCO DIAMOND HARD is allowed to puddle and dry on the surface, a white residue may form that can only be removed by mechanical means such as grinding or sanding. Prevent this by completely distribute or remove all excess EUCO DIAMOND HARD from the surface when application is complete. Allow the first coat to dry for at least 30 minutes before burnishing with a high speed burnishing machine. The second coat will be at a coverage rate of 200 – 400 ft²/gal (4.9 – 9.8 m²/L). Again, do not let the Euco Diamond Hard puddle. Allow the second coat to dry for at least 30 minutes before burnishing with a high speed burnishing machine. Care should be taken to protect the surrounding flooring during applications Do not track EUCO DIAMOND HARD onto untreated concrete, as permanent footprints or tire marks can result.

After the two burnishing applications of Euco Diamond Hard, a standard application Ultraguard followed by high speed burnishing should be performed to further protect the floor.

WARRANTY: The Euclid Chemical Company (“Euclid”) solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid’s installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid’s products for the Buyer’s intended purposes.