

WATER REDUCERS

Master Format #: 03 30 00 03 40 00 03 70 00

EUCON™ WR

WATER REDUCING ADMIXTURE



EUCLID CHEMICAL

PRODUCT INFORMATION

PACKAGING

Packaged in bulk, 275 gal (1041 L) totes, 55 gal (208 L) drums and 5 gal (18.9 L) pails

SHELF LIFE

1 year in original, unopened container

SPECIFICATIONS/COMPLIANCES

ASTM C494, Type A & D

AASHTO M194

DESCRIPTION

EUCON WR is a water reducing, normal set admixture for concrete made from a solution of modified salt of lignosulfonic acid. It provides a more plastic and cohesive mix in the fresh concrete and better durability, reduced shrinkage and less permeability in the hardened concrete. EUCON WR contains no added chlorides or chemicals known to promote the corrosion of steel.

PRODUCT CHARACTERISTICS

FEATURES & BENEFITS

- Provides easier handling and finishing
- Increases strength
- Provides increased durability
- Reduces shrinkage and permeability

PRIMARY APPLICATIONS

- Ready mixed concrete
- Prestressed concrete
- Precast concrete
- Lightweight concrete
- Expansive concrete



PRECAUTIONS/LIMITATIONS

- Care should be taken to maintain EUCON WR above freezing; however, freezing and subsequent thawing will not harm the material if thoroughly agitated.
- Add to mix independent of other admixtures.
- In all cases, consult the Safety Data Sheet before use.

TECHNICAL INFORMATION

PERFORMANCE DATA

The following test results were achieved using typical ASTM C494 mix design requirements, 517 lb/yd³ (307 kg/m³) cement content and similar (± 0.5)% air content. These results were obtained under laboratory conditions with materials and mix designs meeting the specifications of ASTM C494. Changes in materials and mix designs can affect the dosage response.



DIRECTIONS FOR USE

EUCON WR is typically used at dosages of 2 - 10 fl oz/100 lbs (130 - 650 mL/100 kg) of cementitious materials. Higher dosages are acceptable with prior testing and confirmation of the desired performance with specific materials being used.

EUCON WR admixture has been tested per ASTM C494 at a Type A dosage of 4 oz/100 lbs (260mL/100 kg) of cementitious materials and at 8 oz/100 lbs (520 mL/100 kg) of cementitious materials for Type B and D requirements.

Because of variations in job conditions and concrete materials, dosages other than the recommended amounts may be required. In such cases, contact your local Euclid sales representative. EUCON WR should be added to the initial batch water of the concrete mixture. Do not dispense onto dry cement.

Rev. 03.21

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.