



ACCELGUARD® STANDARD

ACCELERATING ADMIXTURE FOR CONCRETE

EUCLID CHEMICAL

DESCRIPTION

ACCELGUARD STANDARD is a chloride based, multi-purpose concrete admixture designed to accelerate the normal setting time of concrete. ACCELGUARD STANDARD improves the plastic and hardened properties of concrete such as workability, compressive and flexural strengths, and freeze-thaw resistance. ACCELGUARD STANDARD densifies concrete and reduces its permeability. ACCELGUARD STANDARD is compatible with water reducing agents and air-entraining agents but should be added separately to the concrete mix.

PRIMARY APPLICATIONS

- General purpose ready-mixed concrete
- Miscellaneous precast concrete
- Manufactured concrete products

FEATURES/BENEFITS



- Reduces initial set time
- Cuts construction costs-no cold weather delays
- Densifies concrete
- Minimizes bleeding and segregation

TECHNICAL INFORMATION

Performance Data

The following test results were achieved using typical ASTM C 494 mix design requirements, 517 lb/yd³ (307 kg/m³) cement content and similar (± 0.5)% air content.

These results were obtained under laboratory conditions with materials and mix designs meeting the specifications of ASTM C 494. Changes in materials and mix designs can affect the dosage response of ACCELGUARD STANDARD.



PACKAGING

ACCELGUARD STANDARD is packaged in bulk, 275 gal (1041 L) totes, 55 gal (208 L) drums and 5 gal (18.9 L) pails.

SHELF LIFE

2 years in original, unopened container.

SPECIFICATIONS/COMPLIANCES

- Fully complies with ASTM C 494, Type C
- Fully complies with AASHTO M 194
- HUD Minimum Property Standards 4901.1 Section 503.2
- New York Board of Standards and Appeals Calendar No. 714-72SM

DIRECTIONS FOR USE

The typical dosage range for ACCELGUARD STANDARD is 16 - 32 oz per 100 lbs (1040 - 2090 mL/100kg) of cementitious material. Higher dosages are acceptable with prior testing and confirmation of the desired performance with specific materials being used.

ACCELGUARD STANDARD should be added to the initial batch water of the concrete mixture. Do not dispense onto dry cement. For ambient temperatures below 50°F (10°C) follow ACI 306 Cold Weather Requirements.

PRECAUTIONS/LIMITATIONS

- Prevent concrete from freezing until a minimum of 1000 psi (7 MPa) is achieved.
- ACCELGUARD STANDARD contains calcium chloride. It is not recommended for use in prestressed, post-tensioned, or structural steel-reinforced concrete.
- In all cases, consult the Safety Data Sheet before use.

Rev. 11.14

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.