



EUCON X15

MID-RANGE WATER REDUCING ADMIXTURE

DESCRIPTION

EUCON X15 is a mid-range water-reducing and plasticizing admixture for concrete. EUCON X15 shows improved finishing characteristics when compared to other commonly used Type A (typically 5 to 6% water reduction) or Type F (typically 12 to 15% water reduction) admixtures. This mid-range approach to water reducing admixtures allows for a wide range of usable dosage rates for a broad application spectrum. EUCON X15 as produced, should be used as received and does not contain calcium chloride.

PRIMARY APPLICATIONS

- Flatwork concrete
- Architectural concrete
- General purpose ready mixed concrete
- Concrete containing fly ash and other pozzolans

FEATURES/BENEFITS

Plastic Concrete



- Produces concrete with lower water:cement ratio allowing for increased strength
- Increased concrete strength lowers the potential for cracks
- Lower water:cement ratio allows for lower cement content, saving the producer money
- Increases concrete workability allowing for easier concrete placement
- Produces concrete that is easier to finish which lowers labor costs

TECHNICAL INFORMATION

Performance Data

The following test results were achieved using typical ASTM C 494 mix design requirements, 517 lb/yd³ (307 kg/m³) cement content and similar (± 0.5)% air content.

These results were obtained under laboratory conditions with materials and mix designs meeting the specifications of ASTM C 494. Changes in materials and mix designs can affect the dosage response of EUCON X15.



PACKAGING

EUCON X15 is packaged in bulk, 275 gal (1041 L) totes, 55 gal (208 L) drums, and 5 gal (18.9 L) pails.

SHELF LIFE

1 year in original, unopened container.

SPECIFICATIONS/COMPLIANCES

EUCON X15 meets or exceeds the requirements of:

- ASTM C 494, Type A and Type F
- AASHTO M 194

DIRECTIONS FOR USE

EUCON X15 is typically used at dosages of 4 to 15 oz per 100 lbs (260 to 1000 mL per 100 kg) of cementitious material. Dosage recommendations depend on the characteristics of the materials being used in the mix design. Higher dosages are acceptable with prior testing and confirmation of the desired performance with specific materials being used.

EUCON X15 should be added to the initial batch water when possible. It should not come in contact with dry cement or other admixtures until they are mixed with the concrete batch.

Field testing is strongly recommended to optimize dose range and performance expectations with local materials.

EUCON X15 is compatible with Euclid Chemical admixtures.

PRECAUTIONS/LIMITATIONS

- Care should be taken to maintain EUCON X15 above freezing; however, freezing and subsequent thawing will not harm the material if thoroughly agitated. Never agitate with air or an air lance.
- Add to mix independent of other admixtures.
- In all cases, consult the Safety Data Sheet before use.

Rev. 11.14

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.